

Test Drive		Value
Viscosity Brookfield 20 rpm @ 25 ° C	cps	18000 - 45000
Density @ 25 ° C	g/ml	1,015 to 1,075
Cold Flexibility @ -5 ° C		meets
Solids	%	57 - 62
Elongation	%	100 minimum
Elongation after weathering 1100 hours		70 minimum
Accelerated weathering 1500 hours		meets
Runoff in thickness of 10 mm		without runoff
Tack (40 mils wet)	minutes	15 -30
Total drying (40 mils in wet)	Hours	1 to 2

* Governed by the standard ASTM D 6083