

# 7922

VERTICAL ADDITIVE

## Ficha técnica

### PRODUCT DESCRIPTION

7922 is a vertical additive for wide variety of urethane to enhance the sag resistant properties of the coating material.

### PRODUCT NUMBER AND COLOR

Standard color is: 7922 Amber

### USAGE CHART

7922 can be used for the following urethane coating products with a 30 minute induction time.

Products	7922/5 gals	Sag Resistance (mls)
7401	1/2 pint	16 - 18
7425	2 x 1/2 pints	14 - 16
7430	2 x 1/2 pints	14 - 16
7435	2 x 1/2 pints	14 - 16
7441	2 x 1/2 pints	14 - 16
7442	2 x 1/2 pints	14 - 16
7443	2 x 1/2 pints	14 - 16
7419	1/2 pint	16 - 18
70611	1/2 pint	>50
70612	1/2 pint	>50
70613	1/2 pint	>50
70620	1/2 pint	>50
70405	1/2 pint	12 - 14
70410	1/2 pint	14 -16

\* Prohibida la reproducción parcial o total de este manual.

### PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	9.1 lbs/gal
Weight Solids	ASTM D4209	100%
Volume Solids	Calculated	100%
VOC	EPA Method 24	0.0 g/L
Viscosity	ASTM D2196	100 cps
Flash Point	ASTM D3278	250+°F
Pot Life (mixed with urethane coating @ 75°F and 50% RH)	Calculated	90 - 120 minutes
Shelf Life		1 year
Cure Time @ 75°F and 50% RH	TT-S-00230A	24 hrs

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

### HEALTH AND SAFETY

Before using this product, carefully read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

Tel. 5395 4333  
01 800 2 AL - KOAT  
25 5628

AL-KOAT<sup>MR</sup>  
IMPERMEABILIZANTES



www.al-koat.com