

# HOJA DE SEGURIDAD DE PRODUCTO

## AL-SEAL® SELLADOR DE URETANO

### Polyurethane Al-Seal

Al-Seal is a single component polyurethane based elastomeric sealant which cures under the effect of atmospheric humidity to form a flexible and resistant joint with very good adhesion on most materials.

### AREAS OF APPLICATION

Al-Seal can be used for heavy and light precast panel expansion joints, wood, aluminium and PVC joinery seams, and expansion joints in traditional construction.

Al-Seal is highly recommended for bonding baked clay and concrete roof tiles. This sealant has a good adhesion without primer on other current materials : most lacquered metals, polyester, glass, stone, ceramic tiles.

### TECHNICAL DATA

Appearance:	Pasty
Colors:	Various
Density at 20 °C Black :	1.16 ± 0.05 ; others : 1.18 ± 0.05
Sagging (ISO 7390):	None
Application temperature:	5 to 35 °C
Skin formation time at 23 °C and 50 % HR:	Ca. 70 min
Cure time at 23 °C and 50 % HR:	3 mm/24 h
Final Shore A hardness (ISO 868 - 3 seconds):	Ca. 40
Modulus at 100 % (ISO 8339):	Ca. 0.4 MPa
Elongation at break (ISO 8339):	> 500 %
Tear strength (DIN 53515):	Ca. 10 N/mm
Temperature resistance:	- 40 to + 80 °C
Resistance to dilute acids and bases:	Average
UV resistance:	Good
Water and salt spray resistance:	Excellent
Compatibility with paints	Water based : yes Solvent based : carry out tests beforehand

**AL-KOAT**<sup>MR</sup>  
IMPERMEABILIZANTES

# HOJA DE SEGURIDAD DE PRODUCTO

## AL-SEAL<sup>®</sup>

### SELLADOR DE URETANO

Specific data	Modulus at 100 % (ISO 37) : ca. 0.3 MPa Modulus at break (ISO 37) : ca. 1.4 MPa Elongation at break (ISO 37) : > 600 %
VOC	0%

#### INSTRUCTIONS FOR USE

##### Substrates preparation :

The substrates must be clean, even, dry, free of dust, oil, grease and any contaminants that could harm bonding.

Check the compatibility of the solvent used with the substrates.

When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer or supplier.

If necessary, rub down metal surfaces beforehand. After rubbing down, the surface should be re-cleaned. Allow the substrate to dry after degreasing.

We recommend to clean concrete with a metal brush.

##### Caulking :

Al-Seal can be applied by a manual or pneumatic gun.

After application, use a putty knife to smooth the joint with soapy water.

This product should be used within 24 hours of opening the cartridge or sausage ; otherwise, the sealant could harden inside. Do not apply at a temperature under 5 °C.

In cold weather, store the cartridges at about 20 °C before use.

Avoid any contact with non-cured MS, hybrid PU or silicone sealants as well as with alcohols or ammonia during curing.

##### Cleaning :

Tools should be cleaned with acetone before the sealant has completely cured. After curing, abrasion is necessary.

#### CONSUMPTION (for a cartridge of 310 ml)

Tube (mm)	2	3	4	5	6	7	8	9	10
Length of cord (m)	98	43	24	15	11	8	6	4	3

#### STORAGE AND SHELF LIFE

12 months in the original, hermetically sealed packagings between 5 and 25 °C

**AL-KOAT<sup>MR</sup>**  
IMPERMEABILIZANTES

# HOJA DE SEGURIDAD DE PRODUCTO

## **AL-SEAL<sup>®</sup>** **SELLADOR DE URETANO**

### **SAFETY**

Not classified as hazardous. Read the material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application.

Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

**AL-KOAT<sup>MR</sup>**  
IMPERMEABILIZANTES

Tel. 5395 4333  
01 800 2 AL - KOAT  
25 5628

[www.al-koat.com](http://www.al-koat.com)