



Date: October 9, 2014  
From: Technical Department

### Testing Results

Product	Color	Use	% Solar Reflectance	Emittance	SRI
7251	White	Roofing	83.0	0.87	103.8
7261	White	Roofing	78.5	0.94	99
7261*	White Granules	Roofing	64.3	0.93	78
7430	Gray	Deck Coating	26.1	0.91	27
7430-11	Light Gray	Deck Coating	38.3	0.91	43
7430-28	White	Deck Coating	74.5	0.90	93
7435	Tan	Deck Coating	40.8	0.91	47
7441	Gray	Roofing	37.6	0.89	42
7442	Tan	Roofing	41.5	0.93	49
7443	White	Roofing	82.0	0.87	102.4
7470-011	Light Gray	Deck Coating	65.9	0.91	81
7490-01	White	Roofing	78.0	0.88	96
7860-01	White	Roofing	65.8	0.92	81
7860-01 w/granules	White	Roofing	53.0	0.94	64
7860-CA	White	Roofing	85.4	0.92	107
7860-LO	White	Roofing	84.0	0.88	105
45080	White	Metal Roofing	82.1	0.94	103
70607	White	Roofing	80.1	0.94	101
70611-16	Ivory	Roofing	72.1	0.93	89
70613	White	Roofing	78.3	0.93	98
70613*	White Granules	Roofing	62.6	0.95	77
70613-CA	White	Roofing	80.0	0.95	101
70613-Bio	White	Roofing	76.4	0.95	95
70613-Bio*	White Granules	Roofing	59.4	0.95	72
70630	White	Roofing	78.8	0.93	99
70680	White	Roofing	77.1	0.94	96
70680/85	White	Roofing	70.8	0.94	88
FC7520	Gray	Deck Coating	27.2	0.93	29
FC7530-00	White	Deck Coating	83.2	0.93	105
FC7530-11	Light Gray	Deck Coating	37.8	0.91	43
FC7540	Gray	Deck Coating	26.9	0.93	29
Acrylithane HS2	White	Topcoat	73.0	0.92	91

\* Applied at 24 wet mils with Lucas (#11 Bright White Dust Free) granules at an application rate of 30 lbs. per 100 square feet.

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 07212011/HSR-TETReport.indd

NEOGARD Div. of JONES-BLAIR